



CHEMICAL RESISTANCE GUIDE

Chemical testing as per ASTM F903 procedure C — as received

Description: 5 minutes at ambient temperature,
1 minute @ 2 psi and 54 minutes at ambient temperature.

CHEMICAL	CONCENTRATION	PROTECTION (minutes)
Acetonitrile	99.9%	>60
Formaldehyde	37%	>60
Kerosene	NEAT	>60
Ethanolamine	99%	>60
Hydrochloric acid	37.3%	>60
Hydrofluoric acid	48%	>60
Hexanes saturated	Saturated	>60
Sodium Hydroxide	70%	>60
Sodium Hypochlorite	5.25%	>60
Nitric acid	70%	>60